



Booth-a-Peel Product Data Sheet 2014 V2

Booth-a-Peel is formulated for the temporary protection of spray booths to help prevent costly & time consuming clean-up methods. Currently there are various types of `paint booth` coatings however with varying degrees of difficulties in removal procedures.

Booth-a-Peel is manufactured under stringent quality control procedures using the latest testing methods,

Appearance	White (liquid state) White (dry state)
Solids percentage by weight	41-60%
PH Value	6-8
Viscosity	Thixotropic
Specific Gravity	1.05 Kgs/litre
Clean-up	Water
Recommended substrates for application Recommended PPE must be used while painting in any enclosed / semi-enclosed area/s.	Suitable for spray booths, paint booths and fixtures commonly found in paint booth areas. Booth-a-Peel may be used over glass lighting fixtures with minimal change to visual lighting. All other surfaces - trial prior to application to ensure Booth-a-Peel suitability. Booth-a-Peel is water-based, environmentally friendly & may be disposed of in landfill.



Booth-a-Peel Product Data Sheet 2014 V2

Coating Thickness	100um dry	150um+ dry
Drying Time	60-90mins @ 25degrees Celsius	75-120mins @ 25 degrees Celsius
Recommended Application Temperature	5-50 degrees Celsius	5-50 degrees Celsius
Removal Temperature Range	5-50 degrees Celsius, water aids release	5-50 degrees Celsius, water aids release
Removal in cold temperatures	Use warm water to aid release	Use warm water to aid release
Removal in extreme heat	Use cold tap water to aid release	Use cold tap water to aid release
Maximum Internal Exposure	<12months	<18months

DISCLAIMER: Booth-a-Peel should only be used in accordance with the information on this data sheet or on the container label. Incorrect application of this product or application onto unsuitable surfaces is beyond the manufacturers control. Liability is restricted to the replacement of material proven faulty. The manufacturer or Distributor is not responsible for any loss or damage arising from incorrect use.