



## Multi Peel Product Data Sheet 2014

Multi Peel is formulated for the temporary protection of most non-porous surfaces during the construction phase to help eliminate damage to expensive surfaces & reduce the cleaning process. Multi Peel is manufactured under stringent quality control procedures using the latest testing methods.

Appearance	Milky (liquid/greyish state) Translucent (dry state)
Solids percentage by weight	41-60%
PH Value	7-10
Viscosity	Thixotropic
Specific Gravity	1.03 Kgs/litre
Clean-up	Water
<p>Recommended substrates for application</p> <p>Recommended PPE must be used while painting in any enclosed / semi-enclosed area/s.</p> <p>10-13mm polyester roller nap for benchtops &amp; floors, 32mm roller naps for roof sheeting. Load roller regularly to ensure minimum 170um + wet.</p>	<p>Acrylic, fiberglass &amp; steel baths, Perspex, stainless steel, chrome, sealed tiled surfaces, grout, concrete surfaces (new), laminate, reconstituted stone, ceasarstone, sealed &amp; fully cured timber, rubber, plastic, colorbond &amp; powdercoated steel. Multi Peel does not contain ammonium traces within the dried peelable film. All other surfaces- trial prior to application, observe application thickness for successful removal 170um + wet</p>



## Multi Peel Product Data Sheet 2014

Coating Thickness	100um dry	150um+ dry
Drying Time (ambient 25degrees C)	30-60mins @ 25degrees Celsius	40-80mins @ 25 degrees Celsius
Recommended Application Temperature	5-50 degrees Celsius	5-50 degrees Celsius
Removal Temperature Range	5-50 degrees Celsius, water aids release	5-50 degrees Celsius, water aids release
Removal in cold temperatures	Use warm water to aid release	Use warm water to aid release
Removal in extreme heat	Use cold tap water to aid release	Use cold tap water to aid release
Maximum Exposure Internally	<12months	<18months

**DISCLAIMER:** Multi Peel should only be used in accordance with the information on this data sheet or on the container label. Incorrect application of this product or application onto unsuitable surfaces is beyond the manufacturers control. Liability is restricted to the replacement of material proven faulty. The manufacturer or Distributor is not responsible for any loss or damage arising from incorrect use.